(19) World Intellectual Property Organization International Bureau





(43) International Publication Date 21 April 2005 (21.04.2005)

PCT

(10) International Publication Number WO 2005/036225 A1

(51) International Patent Classification7:

G02B 6/255

(21) International Application Number:

PCT/SE2004/001442

- (22) International Filing Date: 8 October 2004 (08.10.2004)
- (25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

0302696-0

10 October 2003 (10.10.2003) SE

- (71) Applicant (for all designated States except US): FUTURE INSTRUMENT FIBER OPTICS AB [SE/SE]; Solna Strandväg 20, S-171 54 Solna (SE).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): MENDEL, Richard [SE/SE]; John Bergs Plan 2, S-112 50 Stockholm (SE). RYLANDER, Robert [SF/SE]; Pjäsbacken 12, S-174 58 Sundbyberg (SE).
- (74) Agent: BERGENSTRÄHLE & LINDVALL AB; P.O. Box 17704, S-118 93 Stockholm (SE).


- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: AUTOMATIC CURRENT SELECTION FOR SINGLE FIBER SPLICING



(57) Abstract: In fusion splicing ends of two optical fibers (3) an electric glow discharge between two electrodes (7) is used for heating the ends. In a simple method that can be implemented in automatic fusion splicers, an optimal fusion current that is to pass between the electrodes to give an optimal heating is for ambient conditions is determined by first, in a calibration procedure in the factory, determining an optimal current for splicing ends of some test optical fibers. Then a value of the intensity of light emitted from the ends of the test optical fibers is determined when they are spliced using the optimal parameters. In the field, in generally ambient conditions different from those in the factory, a value of the current required to heat a piece of the test fibers to emit light of an intensity agreeing with that determined for the test fibers in the factory. A proportional change is calculated by mathematically dividing the value of the current required for heating the test fiber in the field conditions by the optimal current determined in the factory. A value of the fusion current to be used in splicing the fiber to each other is calculated by modifying, by the calculated proportional change, the fusion current that should be used for fibers in the factory ambient conditions. Finally, the fusion current used in the actual splicing of the ends of the two optical fibers to each other is controlled to take the calculated value.

